Carbonation Behavior of Powdered Cement-Based Materials Under Different Relative Humidities and CO₂ Concentrations

Kiyofumi Nakada¹, Katsuhito Komiya², Hikaru Fumino², Yuhei Nishio², Manabu Kanematsu² and Takafumi Noguchi³

¹ Department of Building Materials and Components, Building Research Institute, 1 Tachihara, Tsukuba-shi, Ibaraki-ken 305-0802, Japan, nakada@kenken.go.jp

² Department of Architecture, Graduate School of Science and Technology, Tokyo University of Science, 2641 Yamazaki, Noda-shi, Chiba-ken 278-8510, Japan, manabu@rs.tus.ac.jp

³ Department of Architecture, Graduate School of Engineering, The University of Tokyo, 7-3-1 Hongo, Bunkyo-ku, Tokyo, Japan, noguchi@bme.arch.t.u-tokyo.ac.jp

Abstract. *The aim of the current study is to investigate the carbonation behavior of cement hydrates at different environments. Hardened cement pastes are prepared using OPC and BFS and crushed into ~90µm powder. The powder samples are carbonated at 5/20% CO₂ and at 60/85%RH. TGA, XRD and phenolphthalein tests are conducted before and after carbonation. The results show that CH remain uncarbonated even after CO₂ uptake apparently ended and that the amount of the residual CH affects the results of phenolphthalein test. External humidity strongly affects the carbonation behavior of both CH and other hydrates. The degree of CH carbonation is greater at higher humidity, while the degree of other hydrates carbonation is greater at lower humidity. This conflicting effect can occur at surface of bulk concretes and changes in its properties (coarsening of pore structure and cracking) can be caused without apparent carbonation detected by phenol phthalein test. The effect of relative humidity on CSH carbonation should be taken into consideration when estimating long-term performance of carbonated concretes.*

Keywords: Carbonation, OPC, BFS, Relative Humidity, Phenolphthalein Test.

1 Introduction

Carbonation of concrete leads to significant changes in its chemical and physical properties. During the process, gaseous CO₂ diffuses through pore network of concrete and react with cement hydrates. When Portlandite (CH) is carbonated and consumed, pH value of pore water decreases, which causes depassivation of steel bars embedded in RC structures. CH carbonation also contributes to reduction in concrete porosity because precipitated calcium carbonate (C⁺) clogs up the pore space. The clogging of porosity results in a decrease of diffusion path, which improves weight transport resistance in general (Houst *et al.*, 1994). In terms of porosity change, it has been reported that carbonation of calcium silicate hydrate (CSH) has greater impact than CH carbonation (Morandau *et al.*, 2014). CSH carbonation also alters pore size distribution of cement pastes, which can cause coarsening of pore structure (Auroy *et al.*, 2014). Furthermore, it has been known that CSH carbonation is responsible for carbonation shrinkage and subsequent cracking (Chen *et al.*, 2006).

Summarizing the above, carbonation reaction of cement hydrates governs the property changes of carbonated concrete. Better understanding on both the reaction behavior and the impacts can help us to estimate the long-term performance of carbonated concretes. Up to the

present, the impacts of cement hydrate carbonation has been widely investigated (Borges *et al.*, 2010; Auroy *et al.*, 2014), and the changes in physical properties can be related to the degree of carbonation (Morandeau *et al.*, 2014). On the other hand, data on carbonation behavior of cement hydrates are lacking.

As has been already known, carbonation behavior of cement hydrates is strongly affected by external environment (Castellote *et al.*, 2009; Galan *et al.*, 2013). Thus, the aim of the current study is to investigate the carbonation behavior of cement pastes at different humidity and CO₂ concentration. Also, cement hydrates inside bulk concretes are carbonated under changing environments (humidity and CO₂ concentration), because concrete carbonation basically occurs during drying process. In order to estimate the carbonation degree at any environment, it is desirable to remove the bulk effect and to obtain direct relationship between the carbonation degree and external environments. Considering the above, powdered samples (hardened cement pastes) are employed in this study.

2 Materials and Experiments

3 types of cement pastes were prepared. 2 of them were made with OPC (LOI: 0.97%, SiO₂: 21.41%, Al₂O₃: 4.84%, Fe₂O₃: 3.20%, CaO: 65.01%, MgO: 1.08%, SO₃: 2.02%) and their water to cement ratio were 0.45 and 0.60 (N45 and N60). The other was made with OPC and BFS (50:50) and its water to cement ratio was 0.60 (BB60). The pastes were cast into prismatic molds (40×40×160mm) and demolded after 24 hours. They were cured until 91 days under water, and then crushed into powder. In order to uniform their particle size, crashed powders were sieved with 90μm mesh. The powder samples were dried in N₂-purged desiccators, where temperature and humidity were controlled at 20°C and 60/85%RH. After drying, the samples were carbonated at 4 different environments (Relative humidities were 60/85% and temperature was 20°C, CO₂ concentrations were 5/20%, and they are denoted as 6005, 6020, 8505 and 8520.). In order to monitor CO₂ uptake rate, sample weight was measured during carbonation, and the tests were finished after 24 hours at CO₂ concentration of 20% and 72 hours at CO₂ concentration of 5%.

After accelerated carbonation, TGA tests were performed on carbonated and non-carbonated samples. Measurement temperature ranged from 105°C to 1050°C at the heating rate of 10°C/min. The amount of CH and C⁺ were calculated from TG curves and their decomposition was detected from inflection point of ΔTG curves around 400°C to 550°C and 550°C to 800°C. Before the tests the samples were soaked in acetone for 48 hours and dried in vacuum desiccator. XRD tests were also performed on the same samples. Patterns were obtained from 2θ of 5° to 65°. In addition to TGA and XRD tests, phenolphthalein tests were carried out so as to compare apparent carbonation and the degree of carbonation. The powders are packed into sample holder (10×10×0.2mm), and phenolphthalein solution was dropped onto them. Sample color was measured by means of color difference meter before and after phenolphthalein was dropped.

3 Results

3.1 Weight Change and CO₂ Uptake

Figure 1. shows the results of monitoring of the sample weight during carbonation at 5% CO₂ concentration. Sample weight shapely increased in first 8 hours, but the change slowed down

quickly and was completed within 24 hours in most samples. The weight increase is mainly due to CO_2 uptake and evaporation of water generated through carbonation reaction. In the case of OPC system, larger amount of CO_2 was absorbed when water to cement ratio and external humidity is higher. On the other hand, little difference can be found in OPC-BFS system, although gentle weight increase continued after 24-hour carbonation at 60% RH. In Figure 2, influence of CO_2 concentration on the weight change is compared. As expected, increase in sample weight was higher when CO_2 concentration is higher. and the influence is more obvious in higher relative humidity.

Figure 1. Sample weight monitored during carbonation (5% CO_2).

Figure 2. Weight change after carbonation. Carbonation time was 24 hours for 20 % CO_2 and 72 hours for 5% CO_2 .

3.2 Carbonation Behavior of Cement Hydrates

Figure 3. shows the results of TGA tests before and after carbonation. In some cases, especially in lower relative humidity, CH dose not reach full carbonation even after CO_2 uptake apparently stopped (Figure 1.). It has been pointed out that degree of CH carbonation is strongly affected by external humidity and that larger amount of CH is carbonated in more humid environment (López-Arce *et al.*, 2011; Galan *et al.*, 2015). In Figure 3, the results of 5% CO_2 concentration are coincide with the reported behavior of CH carbonation, although little difference can be found in the residual CH of 20% CO_2 concentration.

In addition to the TGA results, the amount of $\text{CC}^{\hat{c}}$ generated from CH carbonation ($n_{\text{CC}^{\hat{c}}}^{\text{CH}}$) and other hydrates carbonation ($n_{\text{CC}^{\hat{c}}}^{\text{others}}$) is calculated using the following equations.

$$n_{\text{CC}^{\hat{c}}}^{\text{CH}} = n_{\text{CH,nc}} - n_{\text{CH,c}} \quad (1)$$

$$n_{\text{CC}^{\hat{c}}}^{\text{others}} = n_{\text{CC}^{\hat{c},c}} - n_{\text{CC}^{\hat{c},nc}} - n_{\text{CC}^{\hat{c}}}^{\text{CH}} \quad (2)$$

Where $n_{\text{CH,nc}}$ and $n_{\text{CH,c}}$ are the amount of CH contained in non-carbonated and carbonated samples respectively (mmol/g). $n_{\text{CC}^{\hat{c},nc}}$ and $n_{\text{CC}^{\hat{c},c}}$ are the amount of $\text{CC}^{\hat{c}}$ before and after carbonation (mmol/g).

The calculation results (grey and yellow lines in Figure 3.) illustrate that relative humidity also has impact on other hydrates carbonation. In most cases, larger amount of $\text{CC}^{\hat{c}}$ is generated from other hydrates at 60% RH than at 85% RH, and the amount of $\text{CC}^{\hat{c}}$ from other hydrates exceeds that from CH carbonation at 60% RH. This general tendency is similar to carbonation behavior of synthesized CSH reported elsewhere (Kim *et al.* 1995), where it has been pointed out that CSH carbonation continues longer and greater amount of CO_2 is absorbed at 60% RH than at 80% RH. In summary, higher humidity promotes CH carbonation and larger amount of CH is consumed. On the other hand, lower relative humidity contributes to other hydrate carbonation and larger amount of CH remain uncarbonated.

Figure 3. Changes in the amount CH and $\text{CC}^{\hat{c}}$. The amounts of $\text{CC}^{\hat{c}}$ coming from CH carbonation and other hydrates carbonation are also illustrated in grey and yellow lines.

3.3 Difference in Calcium Carbonate

Figure 4. shows XRD patterns for carbonated and non-carbonated samples. To compare the presence of CH and three polymorphs of CC , only the range from 25° to 35° is shown in the figure. In general, CH peaks do not disappear after carbonation and their peak height is higher when samples are carbonated at 60%RH, which agrees with TGA results. In regard to CC calcite and vaterite peaks are observed in every pattern, but their proportion of peak height is different depending on relative humidity. At Vaterite peak height of 60%RH (orange) is higher, whereas at calcite peak that of 85%RH (grey) is higher. Aragonite can be found only in 5% carbonation (N45_6005 and BB60_6005).

Figure 4. XRD patterns for carbonated (6005, 8505, 6020 and 8520) and non-carbonated (nc) samples. A, C, V and P denote aragonite, calcite, vaterite and portlandite respectively.

Register for free at <https://www.scipedia.com> to download the version without the watermark

3.4 Color Change During Phenolphthalein Test

Table 1. and Figure 5. show the results of the phenolphthalein tests. Here, the color difference before and after phenolphthalein addition is determined based on CIE $L^*a^*b^*$ color space, where a^* coordinate indicates red (positive) or green (negative). The color of non-carbonated samples turns red immediately and Δa^* value reach around 50 whereas, color change of carbonated samples is slower and their Δa^* value is below that of non-carbonated. The results of carbonated samples also indicate that carbonation environment (both external humidity and CO_2 concentration) affects the sensitivity to the indicator, that is to say, Δa^* value is smaller when relative humidity and CO_2 concentration are higher. In addition, the effect of relative humidity is greater than that of CO_2 concentration.

Table 1. Photographs of compacted samples 60 minutes after phenolphthalein indicator was dropped. Color difference index Δa^* (positive: redder and negative: greener) is also shown below each photograph.

	Non-carbonation	carbonated			
		6005	6020	8505	8520
N45	$\Delta a^*=49.8$	$\Delta a^*=46.6$	$\Delta a^*=44.5$	$\Delta a^*=26.6$	$\Delta a^*=24.6$
N60	$\Delta a^*=51.2$	$\Delta a^*=18.9$	$\Delta a^*=14.0$	$\Delta a^*=2.93$	$\Delta a^*=2.64$
BB60	$\Delta a^*=48.4$	$\Delta a^*=3.58$	$\Delta a^*=18.4$	$\Delta a^*=13.6$	$\Delta a^*=12.1$

Figure 5. Changes in Δa^* after phenolphthalein indicator was dropped. Non-carbonated (nc), carbonated at 60%RH and carbonated at 85%RH are illustrated as grey, orange and blue lines respectively.

4 Discussions

Based on the obtained results, carbonation behavior of cement hydrates and their impact on concrete properties are discussed. First of all, the results of weight increase (Figure 2.) do not agree with the increase in $\text{C}\hat{\text{C}}$ amount after carbonation (Figure 3.). In other words, TGA results indicate that less amount of CO_2 is absorbed at 85%RH, whereas the weight increase is greater at 85%RH. According to natural carbonation tests (Galan *et al.*, 2012), larger amount of water is released from CSH when it is carbonated at lower relative humidity (about 38%RH and 58% are compared). Although the carbonation environment is different from that of the current study, this carbonation behavior of CSH can explain the reason for the disagreement in the figures 2 and 3. When the powder samples are carbonated at lower relative humidity, more H_2O can be released from CSH due to drying and weight increase due to CO_2 uptake is canceled.

Regarding to carbonation behavior of CH and other hydrates, the impact of relative humidity is clearly observed. As has been pointed out, CH carbonation is promoted at higher relative humidity (85%RH) and less amount of CH remain uncarbonated. Compared to the results of phenolphthalein test, the amount of residual CH can be related to color change of phenolphthalein. On the other hand, other hydrates carbonation is promoted at lower relative humidity (60%RH). As a result, at 60%RH, other hydrates carbonation proceeds without enough CH carbonation. Because other hydrates carbonation is more responsible for pore structure changes and carbonation shrinkage, changes in cement paste properties can occur without color change of phenolphthalein in such environments.

As mentioned in the first section, carbonation occurs during drying process. Especially around surface of bulk samples or in small samples, drying proceeds immediately. In such situation, carbonation reaction proceeds under lower relative humidity, which leads to other hydrate carbonation without CH carbonation. In the previous research, CO_2 concentration is main factor for CSH carbonation and decomposition (Castellote *et al.*, 2009). Relative humidity also affects CSH carbonation, and this factor should be taken into account when estimating long-term performance of carbonated concretes.

Register for free at <https://www.scipedia.com> to download the version without the watermark

5 Conclusions

- Powdered cement pastes were carbonated in order to investigate the impact of external environment on carbonation behavior of CH and other hydrates.
- The results of weight increase do not agree with that of TGA tests. The disagreement can be related to the effect of relative humidity on stoichiometry coefficient of H_2O CSH carbonation reaction.
- CH remain uncarbonated even after CO_2 uptake apparently end and the amount of the residual CH affects the results of phenolphthalein test. External humidity strongly affects the carbonation behavior of both CH and other hydrates. The degree of CH carbonation is greater at higher humidity, while the degree of other hydrates carbonation is greater at lower humidity. The conflicting effect above can occur at surface of bulk concretes, and changes in its properties (especially coarsening of pore structure and cracking) can be induced without apparent carbonation detected by phenol phthalein test.
- Relative humidity, as well as CO_2 concentration, strongly affects CSH carbonation, and

this factor should be taken into account when estimating long-term performance of carbonated concretes.

ORCID

Kiyofumi Nakada: <https://orcid.org/0000-0003-2744-1669>

Katsuhito Komiya: <https://orcid.org/0000-0001-8331-677X>

Yuhei Nishio: <https://orcid.org/0000-0002-9865-8606>

Hikaru Fumino: <https://orcid.org/0000-0001-9394-7372>

Manabu Kanematsu: <https://orcid.org/0000-0003-2473-0625>

Takafumi Noguchi: <https://orcid.org/0000-0001-6115-2292>

References

- Auroy, M. *et al.* (2015). 'Impact of carbonation on unsaturated water transport properties of cement-based materials', *Cement and Concrete Research. Elsevier Ltd*, 74, pp. 44–58. doi: 10.1016/j.cemconres.2015.04.002.
- Borges, P. H. R. *et al.* (2010). 'Carbonation of CH and C-S-H in composite cement pastes containing high amounts of BFS', *Cement and Concrete Research*, 40(2), pp. 284–292. doi: 10.1016/j.cemconres.2009.10.020.
- Chen, J. J., Thomas, J. J. and Jennings, H. M. (2006). 'Decalcification shrinkage of cement paste', *Cement and Concrete Research*, 36(5), pp. 801–809. doi: 10.1016/j.cemconres.2005.11.003.
- Castellote, M. *et al.* (2009). 'Chemical changes and phase analysis of OPC pastes carbonated at different CO₂ concentrations', *Materials and Structures*, 42(4), 515–525. doi: 10.1617/s11527-008-9399-1.
- Galan, I., Andrade, C. and Castellote, M. (2012). 'Thermogravimetric analysis for monitoring carbonation of cementitious materials Uptake of CO₂ and deepening in C-S-H knowledge', *J Therm Anal Calorim*, 110, 309–319. doi: 10.1007/s10973-012-2466-4
- Galan, I., Andrade, C. and Castellote, M. (2013). 'Natural and accelerated CO₂ binding kinetics in cement paste at different relative humidities', *Cement and Concrete Research. Elsevier Ltd*, 49, pp. 21–28. doi: 10.1016/j.cemconres.2013.03.009.
- Galan, I. *et al.* (2015). 'Assessment of the protective effect of carbonation on portlandite crystals', *Cement and Concrete Research. Elsevier Ltd*, 74, 68–77. doi: 10.1016/j.cemconres.2015.04.001.
- Houst, Y. F. and Wittmann, F. H. (1994). 'Influence of porosity and water content on the diffusivity of CO₂ and O₂ through hydrated cement paste', *Cement and Concrete Research*, 24(6), 1165–1176. doi: 10.1016/0008-8846(94)90040-X.
- Kim, S. *et al.* (2010). 'The effect of relative humidity on the carbonation of cement paste', *Journal of Materials*, 2(254), 18–25. <https://doi.org/10.11451/mukimate1994.2.18>
- López-Arce, P. *et al.* (2011). 'Influence of relative humidity on the carbonation of calcium hydroxide nanoparticles and the formation of calcium carbonate polymorphs', *Powder Technology. Elsevier B.V.*, 205(1–3), 263–269. doi: 10.1016/j.powtec.2010.09.026.
- Morandau, A., Thierry, M. and Dangla, P. (2014). 'Investigation of the carbonation mechanism of CH and C-S-H in terms of kinetics, microstructure changes and moisture properties', *Cement and Concrete Research. Elsevier Ltd*, 56, 153–170. doi: 10.1016/j.cemconres.2013.11.015.

Register for free at <https://www.scipedia.com> to download the version without the watermark