On the fracture models determined by the continuum-strong discontinuity approach

A.E. HUESPE^{1,*}, J. OLIVER¹, M.D.G. PULIDO¹, S. BLANCO¹ and D. LINERO^{1,2}

¹*E.T.S. d' Enginyers de Camins, Canals i Ports, Technical University of Catalonia (UPC), Campus Nord UPC, Mòdul C1, c/Jordi Girona 1-3, 08034 Barcelona, Spain*

²*National University of Colombia, Engineering School, Bogotá, Colombia*

(* Author for correspondence. E-mail: huespe@cimne.upc.es)

Received 23 August 2005; accepted in revised form 6 September 2005

Abstract. The paper focuses on the Continuum Strong Discontinuity Approach (CSDA) to fracture mechanics, and the traction-separation cohesive laws induced from continuum dissipative models as their projections onto the failure interface. They are compared with the cohesive laws commonly used for the fracture simulation in quasi-brittle materials, typically concrete. Emphasis is placed in the analysis of the mechanical stress-strain states induced by the CSDA into the fracture process zone: first when the damage mechanism is initiated and, after, when the cohesive model determines the crack response. The influence of the material parameters, particularly the fracture energy and the initial continuum softening modulus, in the obtained phenomenological responses is also analyzed. Representative numerical solutions of fracture problems are finally presented.

Key words: Continuum strong discontinuity approach, cohesive models, computational fracture mechanics.

1. Introduction

The performance of classical cohesive traction-separation laws in modeling the appearance and progression of fractures is already a well known issue, and their benefits and drawbacks have been established in many works (Hillerborg 1985; Bazant, 2002; Bazant and Planas, 1998; Planas et al., 2003; Bazant and Li 1997). This paper focuses on a more recent modeling environment: the Continuum Strong Discontinuity Approach (CSDA) to fracture mechanics (Simo et al., 1993; Oliver, 1996a, 1996b; Oliver et al., 1999, 2003, 2004; Oliver and Huespe, 2004) and the cohesive models that are projected by that approach, onto the fracture interfaces, as degenerations of continuum (stress vs. strain) dissipative constitutive models. Therefore, in this sense there is a clear connection of the CSDA with the cohesive fracture mechanics. However, in the CSDA those traction separation laws are never explicitly implemented and the analysis is held in a continuum format in all the stages of the fracture process modeling. This work is an attempt of displaying some benefits, regarding the numerical simulation of fracture that can be extracted from this fact, namely:

- The CSDA may reproduce with higher resolution the dissipative phenomena occurring at the fracture process zone. It is not necessary to introduce an

explicit distinction of the continuum behavior in the bulk and the discontinuous behavior in the fracture to model the transition from continuity to discontinuity.

- The so called time continuity (Papoulia et al., 2003) of the traction separation law is automatically achieved in the CSDA with no necessity of encoding the traction separation law.
- Some numerical problems (i.e., oscillations of the traction profiles along the crack paths) typical of cohesive models equipped with large initial dummy stiffness do not appear in the CSDA implemented with embedded strong discontinuity finite elements.
- The continuum dissipative mechanisms naturally modeled in the CSDA translate into smoother stress fields in the neighborhood of the crack path; unphysical results like the *stress mismatch in cohesive models* and the *inconsistent traction profiles* can be completely removed.

In summary, the CSDA could be regarded as a more comprehensive procedure, to model cohesive cracks, than simple traction separation laws introduced in an *ad hoc* manner. As it will be shown by means of some representative simulations, the pay off for the slightly more complex implementation involved in the CSDA, is an increasingly robustness and accuracy of the simulation of the fracture mechanics phenomena.

2. The continuum-strong discontinuity approach (CSDA): overview

Although the CSDA has been widely described by the authors elsewhere (Simo et al., 1993; Oliver, 1996a, 1996b; Oliver et al., 1999, 2003, 2004; Oliver and Huespe, 2004), in this section its main features are summarized, namely: (a) the selection of a target continuum constitutive model to capture the nonlinear dissipative behavior of the material and (b) the use of the so called strong discontinuity kinematics entailing a

Register for free at <https://www.scipedia.com> to download the version without the watermark

2.1. TARGET CONSTITUTIVE MODEL: CONTINUUM DAMAGE

There is no intrinsic restriction about the target continuum constitutive model, other than its adequacy to reproduce the phenomenological observed material behavior. In this sense, plasticity models for metallic or soil materials have been successfully used. Frictional materials failing in tension, like concrete, can be quite appropriately modeled by using continuum damage models and this motivates this particular choice. Let us, then, define an isotropic continuum damage constitutive model (Oliver, 2000), in terms of the following function of density of free energy:

$$\varphi(\boldsymbol{\varepsilon}, r) = \frac{1}{2} \left(\frac{q(r)}{r} \boldsymbol{\varepsilon} : \mathbf{C} : \boldsymbol{\varepsilon} \right); \quad \mathbf{C} = \lambda(\mathbf{1} \otimes \mathbf{1}) + 2\mu \mathbf{I} \quad (1)$$

where $q \geq 0$ and $r \geq 0$ stand for the stress-like and strain-like internal variables, $\boldsymbol{\varepsilon}$ is the strain tensor, $\mathbf{C}$ is the standard elastic constitutive tensor, depending on the Lamé's parameters λ and μ and $\mathbf{1}$ and $\mathbf{I}$ being the unit second and fourth order tensors. The free energy function is then a potential for the stress field $\boldsymbol{\sigma}$ defined as:

$$\sigma = \Sigma(\epsilon, r) = \frac{\partial \varphi(\epsilon, r)}{\partial \epsilon} = \underbrace{\frac{q(r)}{1-d}}_{r} \mathbf{C} : \epsilon = (1-d) \mathbf{C} : \epsilon \quad (2)$$

where $d = 1 - q(r)/r$, $d \in [0, 1]$, is the continuum damage variable. The kinetic equations defining the evolution of the internal variables are described by:

$$\begin{aligned} \dot{q} &= H \dot{r}; \quad \dot{r} = \gamma \\ q(t)|_{t=0} &= q_0 = \frac{\sigma_0}{\sqrt{E}} > 0; \quad r(t)|_{t=0} = q_0 > 0 \end{aligned} \quad (3)$$

where σ_0 is the uniaxial peak stress and the dimensionless material parameter $H(r) \leq 0$ stands for the continuum softening modulus of the model and defines the slope of the curve $q = q(r)$. Then, the loading-unloading conditions:

$$\begin{aligned} \gamma &\geq 0; \quad F_\sigma(\sigma, q) \leq 0; \quad \gamma F_\sigma = 0 \\ F_\sigma(\sigma, q) &= \sqrt{\sigma : \mathbf{C}^{-1} : \sigma} - q \end{aligned} \quad (4)$$

determine a monotonous increase of r , and decrease of q , along the pseudo-time t . In Equation (4) F_σ is interpreted as a damage criterion that describes an elastic domain in the generalized stress space (σ, q) . If a linear softening law is adopted, as it is shown in Figure 1 (left), the stiffness of the material point response (tangent constitutive modulus) during a monotonic one-dimensional loading process, i.e. the $\sigma - \epsilon$ curve slope, is given by HE (see Figure 1, center). Finally, the internal dissipation of the model is a positive quantity: $D = 1/2(q\dot{r} - \dot{q}r) \geq 0$, which assures the thermodynamic consistency of the model.

As this material model is used to reproduce the strain localization phenomenon observed in a bar subjected to traction, by resorting to a distributed cracking concept, the damage is smeared in a band of width $\hat{\ell}$ as shown Figure 1 (right). Then, the total external work per unit of area consumed as to produce the exhaustion of the bar loading capacity, G_f (i.e., the fracture energy) is:

$$G_f = \hat{\ell} \frac{\sigma_0^2}{2E} \left[1 + \frac{1}{|H|} \right] \quad (5)$$

and assuming $|H| \ll 1$, the softening modulus $H < 0$ can be characterized as:

$$H \approx -\hat{\ell} \frac{\sigma_0^2}{2G_f E} \quad (6)$$

Figure 1. Softening modulus, H , and distributed cracking concept.

Equation (6) supplies a physical interpretation for the softening modulus, H , in terms of material fracture properties.

2.2. STRONG DISCONTINUITY KINEMATICS

Let us consider a body occupying a domain Ω in $\mathbf{R}^3$ and a non-smooth displacement field $\mathbf{u}(\mathbf{x})$ defined in it. A jump, across a material surface S , is assumed to appear in this field, which is characterized by the vector $\delta = \mathbf{u}^+ - \mathbf{u}^-$; $\mathbf{u}^+$ and $\mathbf{u}^-$ being the displacements at both sides of S . Here S is regarded as the limit of a sequence of volumes (or slices) S_h , of bandwidth h and containing the surface S : $S = \lim_{h \rightarrow 0} S_h$ (see Figure 2). The strain field (in infinitesimal strain format) compatible with the displacement jump δ has the form (Oliver et al., 2002):

$$\mathbf{e}_S = \mathbf{e}_{\Omega/S} + \lim_{h \rightarrow 0} \frac{1}{h} (\delta \otimes \mathbf{n})^{\text{sym}} \quad (7)$$

where $\mathbf{n}$ is the unit normal vector to S . From now on, subindex $(\bullet)_S$ and $(\bullet)_{\Omega/S}$ refer, respectively, to entities evaluated into domains S_h and its Ω -complement, Ω/S_h . Since $\mathbf{e}_{\Omega/S}$ and δ are assumed bounded, Equation (7) displays the most relevant feature of the so-called *strong discontinuity kinematics*: the singular (unbounded) character of the strains $\mathbf{e}_S$ as h tends to zero.

The continuum constitutive model of Section 2.1 can now be applied to those singular points exhibiting the kinematics given by Equation (7). By evaluating the stresses $\sigma_S = \Sigma(\mathbf{e}_S, r_S)$ and the traction vector, $\mathbf{t}_S = \sigma_S \cdot \mathbf{n}$, in S_h ; equilibrium (momentum balance) requires the traction vector continuity across S , i.e. :

$$\mathbf{t}_S = \sigma_S \cdot \mathbf{n} = \sigma_{\Omega/S} \cdot \mathbf{n} = \mathbf{t}_{\Omega/S} \quad (8)$$

From the bounded character of the stresses in Equation (8), termed *traction continuity condition*, imposes the bounded character of the stress σ_S , even when $\mathbf{e}_S$ is a singular measure. This condition requires redefining the softening modulus in Equation (3), (see (Oliver et al., 2002)):

$$H = h \bar{H}_S \quad (9)$$

which is the so called *continuum softening modulus regularization*. Observe that, by combining Equations (9) and (6) for $\hat{\ell} = h$ one obtains (for a linear softening rule):

$$\bar{H}_S = \frac{H}{h} = - \frac{\sigma_0^2}{2G_f E} \quad (10)$$

Figure 2. Discontinuous displacement field.

which provides the physical meaning of the *intrinsic softening modulus*, $\bar{H}_S$, as a fracture material property.

A very relevant result from this regularization is that the original continuum constitutive model degenerates in a traction–displacement jump law, that is fulfilled at the discontinuity interface S_h (see (Oliver, 2000)), according to:

$$\mathbf{t}_S = \boldsymbol{\sigma}_S \cdot \mathbf{n} = \boldsymbol{\Sigma}(\boldsymbol{\varepsilon}_S(\boldsymbol{\delta}), r_S) \cdot \mathbf{n} = \boldsymbol{\Sigma}_{S,\mathbf{n}}(\boldsymbol{\delta}, r) \quad (11)$$

The constitutive law (11) is normally presented in the literature as a cohesive law relating the displacement jump $\boldsymbol{\delta}$ with the traction vector $\mathbf{t}_S$. It can be interpreted as a projection, or degeneration, of the continuum model (1)–(4) to a cohesive law at the failure interface. Therefore, it inherits some properties of the original continuum damage model. *The use of a continuum constitutive model, like the one in Section 2.1, to reproduce the effects of the corresponding projected cohesive model (11) into the failure interface, is the most distinguishing feature of the CSDA.* That cohesive model is never derived nor implemented but the results at the failure interface S_h are the same than if this had been done. As a counterpart, in the CSDA the volume dissipative effects in the material bulk, and the transition from continuum to discontinuum (the fracture process zone) (Bazant and Planas, 1998) can be easier and more naturally captured from the continuum format of the constitutive model. This, and other consequences and advantages of this approach to model the cohesive behavior of a crack or fracture, will be displayed in next sections.

2.3. ANALYSIS OF THE DEGENERATED COHESIVE MODEL

The cohesive law (11) could have been alternatively derived by proposing a free energy function per unit of area of S , φ_S (surface density energy). Let us consider the limit of the regularized model for the case of vanishing h , or of the: $\Phi_h = h\varphi(\boldsymbol{\varepsilon}_S, r_S)$. We determine φ_S (see (Oliver, 2000)) as the limit of the sequence: $\varphi_S(\boldsymbol{\delta}, \alpha) = \lim_{h \rightarrow 0} \Phi_h(\boldsymbol{\varepsilon}_S(\boldsymbol{\delta}), r_S)$, which for the function in Equation (1), taking into account the strong discontinuity kinematics in Equation (7), results:

$$\begin{aligned} \varphi_S(\boldsymbol{\delta}, \alpha) &= \frac{1}{2} \frac{q(\alpha)}{\alpha} [\boldsymbol{\delta} \cdot \mathbf{Q}^e \cdot \boldsymbol{\delta}] = \frac{1}{2} \frac{q(\alpha)}{\alpha} [(\lambda + 2\mu)\delta_n^2 + \mu\delta_s^2] \\ \mathbf{Q}^e &= \mathbf{n} \cdot \mathbf{C} \cdot \mathbf{n} = (\lambda + \mu)\mathbf{n} \otimes \mathbf{n} + \mu\mathbf{1} \end{aligned} \quad (12)$$

where $\delta_n = \boldsymbol{\delta} \cdot \mathbf{n}$ and $\delta_s = \boldsymbol{\delta} \cdot \mathbf{s}$ are, respectively, the normal and tangential components of the displacement jump, see Figure 2, and the second order tensor, $\mathbf{Q}^e$, is the so called *elastic acoustic tensor* (Willam and Sobh, 1987). The internal variable q is the same than the one defined in Equation (3) for the continuum model, and $\alpha = \lim_{h \rightarrow 0} hr_S$ is the regularized (bounded) counterpart of the strain-like internal variable r_S (we recall that the strain field $\boldsymbol{\varepsilon}_S$ and the corresponding internal strain-like variable r_S are unbounded measures of order $O(1/h)$). Similarly to the continuum model case, the free energy φ_S is used as a potential for determining the traction vector $\mathbf{t}_S$:

$$\mathbf{t}_S = \frac{\partial \varphi_S(\boldsymbol{\delta}, \alpha)}{\partial \boldsymbol{\delta}} = \underbrace{\frac{q}{\alpha}}_{1-\omega} \mathbf{Q}^e \cdot \boldsymbol{\delta} = (1 - \omega) \mathbf{Q}^e \cdot \boldsymbol{\delta} \quad (13)$$

Figure 3. Cohesive degenerated model. (a) Criterion for activation of the dissipative mechanism in the space of generalized forces; (b) Softening response of the traction-separation law.

where $\omega = 1 - q(\alpha)/\alpha$, ($\omega \in (-\infty, 0]$), is a discrete damage variable. The evolution equations for the internal variables are then defined as:

$$\begin{aligned} \dot{q} &= \bar{H}_S \dot{\alpha}; \quad \dot{\alpha} = \hat{\gamma} \\ q(t)|_{t=t_d} &= q_d = \frac{\sigma_d}{\sqrt{E}} > 0; \quad \alpha(t)|_{t=t_d} = 0 \end{aligned} \quad (14)$$

where t_d is the time of onset of local damage (cracking). The loading-unloading conditions read:

$$\hat{\gamma} \geq 0; \quad F_t(t, q) \leq 0; \quad \hat{\gamma} F_t = 0 \quad (15a)$$

$$F_t(t, q) = \tau_t - q; \quad \tau_t = \underbrace{\sqrt{t \cdot (Q^e)^{-1} \cdot t}}_{\text{effective traction}} = \sqrt{\frac{1}{(\lambda + 2\mu)} t_n^2 + \frac{1}{\mu} t_s^2} \quad (15b)$$

From Equations (14) and (15) it can be observed that α is a monotonous increasing function in time ($\dot{\alpha} \geq 0$). Now, F_t is a damage criterion defined in the space of the generalized forces (t, q) - see Figure 3. These conditions can also be placed in the space of generalized displacements by redefining F_t in terms of the variables (δ, α) :

$$\begin{aligned} \hat{\gamma} &\geq 0; \quad F_\delta(\delta, \alpha) \leq 0; \quad \hat{\gamma} F_\delta = 0 \\ F_\delta(\delta, \alpha) &= \tau_\delta - \alpha \\ \tau_\delta &= \underbrace{\sqrt{\delta \cdot Q^e \cdot \delta}}_{\text{effective crack opening}} = \sqrt{(\lambda + 2\mu)\delta_n^2 + \mu\delta_s^2} \end{aligned} \quad (16)$$

From Equation (16), and the aforementioned condition $\dot{\alpha} \geq 0$, α can be interpreted as the maximum effective crack opening along the loading process history.

In a complete process of crack decohesion, the total energy dissipated at the discontinuity surface, W_S , results:

$$\begin{aligned} W_S &= \int_S \left(\int_{t_d}^{\infty} \mathbf{t} \cdot \dot{\delta} \, dt \right) dS = \int_S \underbrace{\left(\int_0^{\infty} q \cdot d\alpha \right)}_{G_f} dS \\ G_f &= \int_0^{\infty} q \cdot d\alpha = \frac{1}{2} \frac{q_d^2}{\bar{H}} = \frac{1}{2} \frac{\sigma_d^2}{\bar{H} E} \end{aligned} \quad (17)$$

which matches the classical concept of Fracture Energy in cohesive models as the consumed energy per unit of the crack area (Bazant and Planas 1998) (see Figure 3b).

Remark 1. Unlike in the crack band model of Bazant (1983), in the CSDA, the softening modulus is not regularized in terms of a characteristic length, ℓ_{ch} , playing the role of a material parameter. Here, though the continuum strain softening regularization (9) introduces the length (h) in the dimension of the regularized softening parameter $\bar{H}$, this length is not a physical property, but a computational regularization parameter as small as permitted by the machine precision.

Remark 2. The cohesive model induced by Equations (12)–(16) belongs to a subclass of the family of cohesive models described by Ortiz et al. in (Ortiz and Pandolfi, 1999). In that framework, the surface free energy density, φ_S , in Equation (12) verifies the material frame indifference requirements:

$$\begin{aligned} \varphi_S(\delta, q) &= \varphi_S(\mathbf{R} \cdot \delta, q); & \forall \mathbf{R} \in Orth^+ \\ \text{or } \mathbf{t}(\mathbf{R} \cdot \delta, q) &= \mathbf{R} \cdot \mathbf{t}(\delta, q); & \forall \mathbf{R} \in Orth^+ \end{aligned} \quad (18)$$

This property is inherited from the continuum free energy density in Equation (12). Furthermore, Ortiz et al. introduce an effective traction τ^{op} :

$$\tau^{\text{op}} = \sqrt{t_n^2 + \beta^{-2} t_s^2} \quad (19)$$

to define the crack loading criteria. The material parameter β in Equation (19) sets the ratio between the normal ($t_n = \mathbf{t} \cdot \mathbf{n}$) and tangential ($t_s = \mathbf{t} \cdot \mathbf{s}$) critical traction components, and it is assumed characterizable by an additional experimental test. On the contrary, in the degenerated cohesive model of Equations (12)–(16), β is predetermined by the elastic parameters of the continuum model as:

$$\beta = \sqrt{\frac{\mu}{\lambda + 2\mu}} \quad (20)$$

as it can be checked from Equation (15b).

Remark 3. Prior to the crack activation, the traction-separation law $\mathbf{t}(\delta)$ induced by the CSDA is naturally inactive, i.e.: the crack remains closed ($\delta=0$) at any material point during the pre-critical (elastic) states. Indeed, in the elastic regime, for the continuum model, the traction continuity condition $\boldsymbol{\sigma}_S \cdot \mathbf{n} = \boldsymbol{\sigma}_{\Omega/S} \cdot \mathbf{n}$ imposes that $\boldsymbol{\varepsilon}_S = \boldsymbol{\varepsilon}_{\Omega/S}$ and, from Equation (7), $\delta=0$. This makes unnecessary the introduction of any kind of dummy stiffness in the traction/separation law, $\mathbf{t}(\delta)$, to enforce the crack closure before the fracturing criterion is fulfilled. As it will be shown in Section 4, the typical oscillatory traction profile displayed by the cohesive models with high dummy stiffness (see Rots (1988), pp. 63, Simone (2004)) does not show up by using the CSDA.

Remark 4. (Time continuity of the traction-separation law): Papoulia et al. (2003) have introduced the notion of *time continuity* related to cohesive laws, within the

context of interface finite element models. The authors advocate that lack of that pseudo-time continuity, in traction/separation laws, leads to numerical instabilities and loss of convergence of the iterative numerical procedure to reach the equilibrium states. This effect cannot be overcome by reducing the time step. Traction/separation laws, introduced after crack activation in an ad hoc manner, do not exhibit, in general, such time continuity, which should be enforced via the so-called *encoding procedure* (Papoulia et al., 2003). On the contrary, in the CSDA any selected continuum constitutive model, $\sigma = \Sigma(\epsilon(t))$, like the one in Equations (1)–(4), is a pseudo-time continuous function and, therefore, the map $t_s \mapsto \sigma_s(t) \cdot \mathbf{n}$ is a time continuous projection, even at the crack activation time t_{loc} :

$$\mathbf{t}_s(t)|_{t=t_{loc}} = \lim_{t \rightarrow t_{loc}} (\sigma_s(t) \cdot \mathbf{n}) \quad (21)$$

Therefore, although the degenerated continuum model in Equations (12)–(16) is a rigid-model (i.e.: the initial secant stiffness in Equation (13) is infinity) and Equation (13) is undetermined at $t = t_{loc}$ (being $\delta(t_{loc}) = 0$ and $\alpha(t_{loc}) = 0$), Equation (21) defines uniquely the traction vector, $\mathbf{t}_s$, at $t = t_{loc}$, which removes that indetermination.

3. Modeling the fracture process zone

A specific feature of the CSDA is that the appearance of damage, in a given material point, can be made not simultaneous to cracking. In fact, in the most general case the material response will initially follow a stable continuum damage process starting at the damage time t_d . In a subsequent time, t_{loc} , loss of positive definiteness of the localization tensor, $\mathbf{Q}^{loc}$, defined in terms of the tangent constitutive operator, $\mathbf{C}^{tan}$ as:

$$\mathbf{Q}^{loc} = \mathbf{C}^{tan} \mathbf{n} \mathbf{n} \quad (22)$$

$$\mathbf{C}^{tan} = \frac{\partial \sigma(\epsilon, r)}{\partial \epsilon}$$

signals the onset of the material instability (Oliver and Huespe, 2004) and the formation of the displacement discontinuity that characterizes the crack. The delay of t_{loc} in front of t_d depends, for a given material model, on the material properties and the stress state. For a given stress state, the less negative is the softening modulus, H in Equation (3), the larger is the interval $[t_d, t_{loc}]$. Therefore, from a phenomenological approach to crack modeling, one can take advantage of this fact to model the amount of volumetric dissipation in front of the crack tip and, indirectly, the size and influence of the fracture process zone. This is sketched in Figure 4: the initial value of the continuum softening modulus, a material property H_{con} , rules the stable damage production at the considered point (see Figure 4a). Material points in this stage, in front of the crack tip, are displayed in the grey zone in Figure 4b, between points **D** (standing for onset of damage) and **L** (standing for onset of localization). The length ℓ_d of this *stable damaged zone* is governed by the value H_{con} as said before. As, at time t_{loc} , material instability is detected the continuum softening modulus is no longer determined as a material property but regularized from the intrinsic softening modulus $\bar{H}$ (in turn depending on the fracture energy) according to Equation (9), see Figure 4a. At the same time, the strong discontinuity kinematics (7) is

Figure 4. (a) Softening rule, (b) Generalized fracture process zone and (c) Regular (RGP) and singular (SGP) Gauss Points in a finite element with embedded discontinuity.

activated, this ensuring fulfillment of the degenerated traction/separation law and the subsequent correct dissipation of the fracture energy G_f up to the complete stress release. Points in this stage are signaled, in Figure 4b, as the *cohesive zone* between points **L** (standing for onset of localization) and **R** (standing for stress release). Both, the stable damage and the cohesive zones, constitute the generalization, in a CSDA setting, of the fracture process zone (FPZ), classically considered in non-linear fracture mechanics (Bazant and Planas, 1998), as the locus of material points where the fracture is processed by dissipation mechanisms. As it will be shown in Section 4.1, the total size of this fracture process zone, ℓ_{FPZ} , basically depends on the amount of fracture energy G_f , and the length of the stable damage zone, ℓ_d (and the corresponding dissipation) is ruled by the continuum softening modulus H_{con} . Therefore, the size of the cohesive zone, ℓ_{loc} , can be expressed as:

$$\ell_{loc}(G_f, H_{con}) = \ell_{FPZ}(G_f) - \ell_d(H_{con}, G_f) \quad (23)$$

Register for free at <https://www.scipedia.com> to download the version without the watermark

In this way the CSDA provides a setting to model the transition from continuum to discontinuum and to characterize the complete fracture process zone.

4. Representative numerical simulations and assessment of the CSDA

The CSDA described in previous sections can be readily implemented in numerical modeling scenarios using an embedded strong discontinuity finite element technique (Oliver et al., 2002). The distinguishing features of finite elements with embedded discontinuities with respect to standard finite elements are essentially two (Oliver and Huespe, 2004): (a) the standard deformation modes are supplemented with additional deformation modes, which reproduce the strong discontinuity kinematics in Equation (7), and (b) besides the standard integration points (the “regular Gauss points”, RGP in Figure 4c) each element is equipped with an additional Gauss point (the “singular Gauss point” SGP in Figure 4c) where the behavior of the discontinuity interface, S , in terms of the kinematics (7) and the softening regularization (9) is reproduced. In addition, the inner traction continuity Equation (8) is enforced in terms of the stresses at the regular and singular sampling points, this providing an

additional equation that resolves the elemental displacement jump. In elastic regimes, this equation is trivially fulfilled with the contributions of the standard deformation modes and, then, the enriching discontinuous displacement modes are not activated.

In the following sections, some well-known, and widely studied, crack propagation problems are modeled in the CSDA context. The simulation is here addressed to present the distinguishing features supplied by the degenerated cohesive model to the numerical solution. In order to reproduce the different tensile and compressive fracture behavior of quasi-brittle materials, like concrete, the continuum damage model of Section 2.1 is slightly modified in the following sense: the damage criterion of equation (4) is switched to:

$$\mathbf{F}_\sigma(\boldsymbol{\sigma}, q) = \sqrt{\boldsymbol{\sigma}^+ : \mathbf{C}^{-1} : \boldsymbol{\sigma}} - q \quad (24)$$

$$\boldsymbol{\sigma}^+ = \sum_{i=1}^3 \langle \sigma_i \rangle \mathbf{p}_i \otimes \mathbf{p}_i$$

where $\boldsymbol{\sigma}^+$ stands for the positive part of the stress tensor $\boldsymbol{\sigma}$, σ_i and $\mathbf{p}_i$ stand, respectively, for the eigenvalues (principal stresses) and eigenvectors of $\boldsymbol{\sigma}$, and $\langle \sigma_i \rangle$ is the positive part of σ_i ($\langle \sigma_i \rangle = \sigma_i$ for $\sigma_i > 0$ and $\langle \sigma_i \rangle = 0$ otherwise). With this modification, damage is restricted to tension dominated states so that the model will be termed **tension damage model**. This feature, imposed in the continuum damage model, is then automatically inherited by the corresponding degenerated traction/separation law without necessity of any ulterior modification.

4.1. THREE-POINT NOTCHED BEAM TEST

The crack propagation problem in a notched concrete beam supported on three points and subjected to a three-point load is considered. The geometry, boundary conditions and material data are similar to those presented by Rots (1988) (p.62). In the present numerical study, a rather fine finite element mesh of linear triangles, with 25 elements discretizing the domain extending from the notch tip to the load application point (≈ 80 mm), is used. In these elements, the main phenomena involved in the crack propagation are going to be captured. The continuum constitutive model is the tension damage model, introduced above, specified for the plane stress case and equipped with a linear softening law. Although tracking procedures for automatic determination of the crack propagation path are available (Oliver et al., 2004; Oliver and Huespe, 2004), here that path has been artificially predetermined as the vertical line starting from the notch tip in order to make the results independent of the determination of that crack path.

4.1.1. Assessment of time continuity

Figure 5 shows the evolution, in terms of the pseudo-time u_y (the monotonically increasing vertical displacement of the load application point), of the normal and tangential components of the traction vector ($\mathbf{t}_S = \boldsymbol{\sigma}_S \cdot \mathbf{n}$) at four different points of the crack path (points A, B, C and D at a distance ζ from the notch tip). There it can be observed that both components of $\mathbf{t}_S$ are continuous all along the

Figure 5. Notched three-point beam test: (a) Problem description, (b) Selected points in the crack path, (c) and (d) Evolution of the normal and tangential traction components.

time, irrespective of the transition from the continuous to crack activated states. This assesses the aforementioned time continuity of the degenerated traction-separation law (see Remark 4).

4.1.2. Action-response smoothness

Figure 6a shows the pseudo-time evolution of the applied force (action-response curve). In Figure 6b, spatial profiles of the normal component of the traction, t_n , along the crack path, as a function of the coordinate ζ , for the different times signaled in Figure 6a, are presented. Unlike what is mentioned in the literature about the oscillatory behavior of the traction components when using cohesive models equipped with large dummy elastic stiffness (Rots (1988), Alfano et al. (2001), Planas et al. (2004)), in the results provided by the CSDA that oscillatory behavior is not observed. The profile labeled t_1 , corresponds to an elastic response during the loading process (at time t_1 all elements are in the elastic range) and, as expected, is smooth. The same smooth response can be observed, in Figure 6b, for all the profiles at subsequent times, even when they involve material points in softening range and also in released stress states (profiles t_2 to t_5). The reason for this is that the traction-separation law (13), induced at the crack by the CSDA via the projection of the continuum constitutive Equation (2), though exhibiting an initial infinite secant stiffness (which would correspond to an infinite value of the dummy stiffness in the cohesive model) is integrated in its continuum format in Equation (2)–(4), without involving that singular initial stiffness (see Remark 3).

Figure 6. Notched three-point beam test: a) Force-displacement curve, b) Profiles of the normal traction component distribution at different stages of the analysis.

4.1.3. Stress mismatch

Another observed problem in classical cohesive models, pointed out by Elices et al. (2002) and Planas et al. (2003) and termed *cohesive model mismatch*, is related to the distribution and properties of the stress states in bulk points at the immediate neighborhood of the crack tip.

These authors observed that, using classical cohesive models and a propagation criterion based on the maximum principal stress, the directions of maximum principal stresses in those points becomes *parallel* to the crack path and their magnitude are *greater than the ultimate tensile stress* σ_u .

Is in this context that the numerical solution in Figure 7, obtained in a CSDA format, is analyzed regarding the role of the initial continuum softening modulus, H_{con} , described in Section 3.

The continuum format of the CSDA allows accounting for the energy dissipation during the loading process in points undergoing stable softening. This leads to the stress state presented, in terms of the principal stress vectors in Figure 7, as the crack propagation length reaches 17% (≈ 17 mm) of the total beam height. There, it can be observed that the stress state at the crack tip neighborhood is, approximately, hydrostatic (both principal stresses are similar) in agreement with the literature. In addition, near the consolidated crack, the largest principal stress holds *orthogonal* to the crack path and *smaller than the peak stress*. The *stress mismatch* is, then, not present in the results. It is also noticed in Figure 7 the existence of a singular point ($\sigma = 0$) nearby the crack tip and in front of it. The appearance of this singular point (all the directions are principal) could be the source of the reported difficulties (see (Mosler and Moschke, 2003) for instance) when tracking algorithms and too coarse finite element meshes are used.

4.1.4. Stress field smoothness

In Figure 8 the stress fields for two limit cases are shown. Figure 8a corresponds to a very small *stable damage zone* achieved by using a very large (negative) value of the initial softening modulus, H_{con} , whereas Figure 8b corresponds to a large

Figure 7. Notched three-point beam test: Principal stress field in the neighborhood of the crack.

stable damage zone achieved by using an almost null (but still negative) initial softening modulus H_{con} . Therefore, results in Figure 8a would match the ones obtained with a classical cohesive model where the behavior in the bulk is assumed totally elastic.

The figures also display, in a grey scale, the elements exhibiting a maximum principal stress larger than the tensile material strength σ_u . Comparison of both figures clearly shows the beneficial effects of the bulk dissipation mechanisms in the smooth character and consistency of the resulting stress fields.

4.1.5. Fracture process zone

Let us focus on the role played by the initial continuum softening modulus, H_{con} of the softening rule in Figure 4a, and its influence on the fracture process zone structure. In order to allow a clearer and more complete development of that fracture process zone, the analysis is carried out on a beam higher than the preceding one (the beam height in Figure 5a is now changed to 0.24m).

Curves in Figure 9a show the dependence of the fracture process zone length, ℓ_{FPZ} , on the fracture energy, G_f , as a function of the material characteristic length parameter ($\ell_{ch} = EG_f/\sigma_u^2$) characterizing the material brittleness (see Elices et al. (2002)). In the figure it can be observed that ℓ_{FPZ} depends clearly on G_f but it barely changes with those substantial changes of H_{con} . Thus, the experiment assesses

Figure 8. Notched three-point beam test. Principal stresses and elements (in a grey scale) with a principal stress larger than the material peak strength. (a) Null stable damage zone (b) Large stable damage zone.

the *exclusive dependence*, stated in Equation (23), of the total length of the fracture process zone on the fracture energy, G_f .

In Figure 9b, it is shown the dependence of the *stable damage zone* size, ℓ_d , with the H_{con} and G_f values. Results are parameterized in terms of the normalized length, χ , ($\chi = -H_{con}\ell_{ch}$). Plots of curves $\ell_d(\chi)$, for different values of $\ell_{ch}(G_f)$, are then presented. In agreement to the assertion in Bazant (1996), about the changing length of the micro cracking zone in front of the crack tip, the numerical simulations show a similar behavior. Therefore, all lengths in Figure 9b have been measured at the time as stresses are completely released at the notch tip (complete stress release). It can be observed that, for a given value of G_f , increasing values of $|H_{con}|$, diminish the stable damage zone size ℓ_d as stated in Equation (23) (the lower bound is, approximately, the size

Figure 9. Fracture process zone development in a three-point bending test of a notched beam: (a) Plots of the fracture process zone lengths, ℓ_{FPZ} , versus the material characteristic length ℓ_{ch} ; (b) Stable damage zone length, ℓ_d , versus the initial softening modulus H_{con} ; (c,d,e) Snap shots of the FPZ (dissipating finite elements in light grey) for different cases.

of one finite element $0.004 \div 0.007$ m). Typical developments of the FPZ, for different material parameter values, are displayed in Figure 9c–e (finite elements undergoing dissipation are plotted in light grey color). There, the *stable damage zone* (round shaped in front the crack tip) can be clearly differentiated from the remaining of the FPZ.

4.2. DOUBLE CANTILEVER BEAM (DCB TEST)

Another typical example of a Mode I crack propagation problem, the double cantilever beam test (DCB) of Figure 10, has been solved considering a plain stress model (of 1m width) with dimensions and material data similar to those presented in Zi et al. (2003). The crack propagation path has been set to the horizontal line starting at the notch tip. A structured finite element mesh, of linear triangles with 7.0 mm side length, has been constructed to model the cohesive zone. This mesh size is one order larger than in the mesh reported in (Zi and Belytschko, 2003).

4.2.1. Predicted peak-load values

This test emphasizes the effects on the predicted peak loads, of the inclusion in the simulation of the stable dissipation zone via the initial continuum softening modulus,

Figure 10. Double cantilever beam test. (a) Geometrical model and material data; (b) load-displacement (CMOD) curves; (c) and (d) normal traction component along the crack path at different times.

H_{con} . Like in previous cases, the problem has been solved using two different procedures. In *Procedure A*, an elastic response is imposed at the bulk, like in standard cohesive models, by using a very large (negative) value of the initial softening modulus, H_{con} (stable dissipation zone does not exist); in *Procedure B*, bulk dissipation is admitted by specifying a softening modulus $H_{\text{con}} \approx 0$ (large stable dissipation zone). In both cases the same value for the fracture energy G_f is considered. Figure 10b displays the corresponding force-displacement (CMOD) curves. It can be checked that allowing dissipation on the bulk has a non-negligible effect on the predicted peak load, in the sense of lowering them.

4.2.2. Consistency of the stress profiles

Figure 10c plots the distribution of the crack normal stress component, t_n , along the crack path (stress profile), at the three different times, t_1 , t_2 and t_3 , specified in the equilibrium curves of Figure 10b. Those curves computed with the *Procedure A* (standard cohesive model) show peak values greater than the material tensile strength ($\sigma_u = 3 \text{ MPa}$). This *inconsistency* has also been detected by Zi et al. (2003) using a similar procedure. These authors claim that this unwelcome effect disappears, or diminishes, with mesh refining. Results obtained with *Procedure B* (bulk dissipation

Figure 11. Double cantilever beam test. Stress stages at different material points

is allowed) show, on the contrary, consistent stress profiles. They are not spike-shaped, as in the previous case, and the maximum stress level remains always below σ_u , even for the relatively coarse mesh used in the analysis.

4.2.3. Fracture stages

Figure 11 shows the evolution of the traction normal component, t_n , provided by the CSDA using the previous *Procedure B*, at three different points A, B and C in the cohesive zone. The abscissa of these curves is the vertical displacement of the load application point, which defines the loading process evolution. There, typical stages in the fracturing process of a material point can be clearly observed: (i) the elastic pre-critic stage, before crack activation, showing increasing values of the stress; (ii) a plateau in the stress evolution corresponding to the stable damage stage in the fracture process zone; (iii) the cohesive stage characterized by the descending branch and (iv) the stress released stage characterized by the final horizontal branch.

5. Conclusions

Along this work, the ability of the CSDA to capture fracture phenomena has been examined. The additional contribution of the CSDA to simulating fracturing processes lies on its intrinsic capability to describe in the same modeling setting (i.e. a unique continuum constitutive model), the dissipation phenomena at both the bulk material and the crack interface. This is achieved by introducing the following specific ingredients:

- The strong discontinuity kinematics (7), the inner traction continuity Equation (8) and the continuum softening regularization (9).
- A more precise description of the fracture process zone in terms of the stable damage zone and the cohesive zone (see Figure 4). Unlike in the standard cohesive models, the continuum format of the CSDA allows considering *dissipation*

in softening materials in a stable (non-localized) mode before singularity of the localization tensor, signaling the onset of a strain discontinuity, takes place (Oliver and Huespe, 2004). One can take advantage of this fact to model that part of the fracture process zone where bulk dissipation occurs which, as it was remarked in Bazant (1996), is not done in standard cohesive models. The specific sizes and influence of both zones can be, then, modeled, for every material, in terms of the following properties defining the softening rule in the continuum model:

- The classical fracture energy, G_f , that governs the total size of the fracture process zone.
- The initial continuum softening modulus, H_{con} , an additional fracturing property to be experimentally determined, that governs the size of the stable damage zone and the corresponding dissipation phenomena at the material bulk. The greater is $|H_{\text{con}}|$ the smaller is the stable damage zone, ℓ_d and, therefore, the total dissipated energy is more approximately described by G_f .
- The use of specific finite elements with embedded discontinuities. They allow capturing the crack propagation, inside the elements, along a crack path that is not *a priori* determined.

The degeneration of the selected continuum constitutive model into a projected traction-separation law at the fracture interface provides a direct link of the CSDA with the classical cohesive models. In this context, it has been shown that some drawbacks and inconsistencies of simulations using standard cohesive models and reported in the literature can be overcome, i.e.:

- The lack of *time continuity* of the traction-separation law and its numerical oscillatory character.
- The *stress mismatch* effect and the lack of smoothness of the stress field near the crack tip.
- The *inconsistency* of the numerical obtained stress profiles exceeding the peak stress.

References

- Alfano, G. and Crisfield, M.A. (2001). Finite element interface models for the delamination analysis of laminated composites: Mechanical and computational issues. *International Journal for Numerical Methods in Engineering* **50**, 1701–1736.
- Bazant, Z.P. (1983). Crack band theory for fracture of concrete presented at Matériaux et Constructions.
- Bazant, Z.P. (1996). Analysis of work-of-fracture method for measuring fracture energy of concrete. *Journal of Engineering Mechanics-Asce* **122**, 138–144.
- Bazant, Z.P. (2002). Concrete fracture models: testing and practice. *Engineering Fracture Mechanics* **69**, 165–205.
- Bazant, Z.P. and Li, Y.N. (1997). Cohesive crack with rate-dependent opening and viscoelasticity: I. mathematical model and scaling. *International Journal of Fracture* **86**, 247–265.
- Bazant, Z.P. and Planas, J. (1988). *Fracture and size effect in concrete and other quasibrittle materials*: CRC Press.
- Elices, M., Guinea, G.V., Gomez, J. and Planas, J. (2002). The cohesive zone model: advantages, limitations and challenges. *Engineering Fracture Mechanics* **69**, 137–163.
- Hillerborg, A. (1985). Numerical methods to simulate softening and fracture of concrete. in *Fracture Mechanics of Concrete: Structural Application and Numerical Calculation*, G. C. S. a. A. D. Tomaso, Ed., pp. 141–170.

- Mosler, J. and Meschke, G. (2003). 3D modelling of strong discontinuities in elastoplastic solids: fixed and rotating localization formulations. *International Journal for Numerical Methods in Engineering* **57**, 1553–1576.
- Oliver, J. (1996a). Modelling strong discontinuities in solid mechanics via strain softening constitutive equations 1. Fundamentals. *International Journal for Numerical Methods in Engineering* **39**, 3575–3600.
- Oliver, J. (1996b). Modelling strong discontinuities in solid mechanics via strain softening constitutive equations 2. Numerical simulation. *International Journal for Numerical Methods in Engineering* **39**, 3601–3623.
- Oliver, J. (2000). On the discrete constitutive models induced by strong discontinuity kinematics and continuum constitutive equations. *International Journal of Solids and Structures* **37**, 7207–7229.
- Oliver, J., Cervera, M. and Manzoli, O. (1999). Strong discontinuities and continuum plasticity models: the strong discontinuity approach. *International Journal of Plasticity* **15**, 319–351.
- Oliver, J., Huespe, A.E. (2004). Continuum approach to material failure in strong discontinuity settings. *Computer Methods in Applied Mechanics and Engineering* **193**, 3195–3220.
- Oliver, J. and Huespe, A.E. (2004). Theoretical and computational issues in modelling material failure in strong discontinuity scenarios. *Computer Methods in Applied Mechanics and Engineering* **193**, 2987–3014.
- Oliver, J., Huespe, A.E., Pulido, M.D.G. and Chaves, E. (2002). From continuum mechanics to fracture mechanics: the strong discontinuity approach. *Engineering Fracture Mechanics* **69**, 113–136.
- Oliver, J., Huespe, A.E., Pulido, M.D.G. and Samaniego, E. (2003). On the strong discontinuity approach in finite deformation settings. *International Journal for Numerical Methods in Engineering* **56**, 1051–1082.
- Oliver, J., Huespe, A.E., Samaniego, E. and Chaves, E.W.V. (2004). Continuum approach to the numerical simulation of material failure in concrete. *International Journal for Numerical and Analytical Methods in Geomechanics* **28**, 609–632.
- Ortiz, M. and Pandolfi, A. (1999). Finite-deformation irreversible cohesive elements for three-dimensional crack-propagation analysis. *International Journal for Numerical Methods in Engineering* **44**, 1267–1282.
- Papoulia, K.D., Sam, C.H. and Vavasis, S.A. (2003). Time continuity in cohesive finite element modeling. *International Journal for Numerical Methods in Engineering* **58**, 679–701.
- Planas, J., Cendon, D., Sancho, J.M., Reyes, E. and Gálvez, J. (2004). Análisis de la respuesta de elementos finitos de intercara en la simulación numérica de fisuras cohesivas. presented at Métodos Computacionais em Engenharia, Lisboa, May 31-June 2, Portugal.
- Planas, J., Elices, M., Guinea, G.V., Gomez, F.J., Cendon, D.A. and Arbilla, I. (2003). Generalizations and specializations of cohesive crack models. *Engineering Fracture Mechanics* **70**, 1759–1776.
- Rots, J.G. (1988). Computational Modeling of Concrete Fractures: Delft University of Technology.
- Simone, A. (2004). Partition of unity-based discontinuous elements for interface phenomena: computational issues. *Communications in Numerical Methods in Engineering* **20**, 465–478.
- Simo, J., Oliver, J. and Armero, F. (1993). An analysis of strong discontinuities induced by strain-softening in rate-independent inelastic solids. *Computational Mechanics* **12**, 277–296.
- Willam, K. and Sobh, N. (1987). Bifurcation analysis of tangential material operators. in *Transient/Dynamic Analysis and Constitutive Laws for Engineering Materials*. vol. **2**, G.N. Pande and J. Middleton, Eds.: Martinus-Nijhoff Publishers. pp. C4/1–13.
- Zi, G. and Belytschko, T. (2003). New crack-tip elements for XFEM and applications to cohesive cracks. *International Journal for Numerical Methods in Engineering* **57**, 2221–2240.