Evaluation of ETICS Characteristics that Affect Surface Mould Development

João L. Parracha^{1,2}, Armand Cortay^{1,3}, Giovanni Borsoi², Rosário Veiga¹ and Lina Nunes^{1,4}

¹ National Laboratory for Civil Engineering, LNEC, Av. do Brasil 101, Lisbon, Portugal, jparracha@lnec.pt, rveiga@lnec.pt, linanunes@lnec.pt

² Civil Engineering Research and Innovation for Sustainability, CERIS, Instituto Superior Técnico, University of Lisbon, 1049-001, Lisbon, Portugal, giovanni.borsoi@tecnico.ulisboa.pt

³ École Nationale D'Ingénieurs de Saint-Étienne, ENISE, Rue Jean Parot 58, Saint-Étienne, France armand.cortay@enise.fr

⁴ Centre for Ecology, Evolution and Environmental Changes, CE3C, Rua Capitão João d'Ávila, Azores, Portugal

Abstract. *External Thermal Insulation Composite Systems (ETICS) are nowadays often used in new constructions but are also one of the most frequently used thermal retrofitting solutions for buildings. These systems have several advantages such as low installation cost, ease of application and increased thermal efficiency. Nevertheless, a number of questions have been raised on their long-time durability particularly related to biodeterioration. Biological growth is strongly influenced by several parameters, such as water content, temperature, pH but also by the type and hygroscopic properties of the building materials. It is therefore essential to understand and correlate those properties with biological growth. This paper aims at evaluating some ETICS characteristics that might influence surface mould development which is recognized as one of the major groups of deteriorating organisms. The susceptibility of the surface finishing layer and thermal insulation to biological growth was assessed through natural inocula and selected fungi and, whenever possible, correlated with water absorption and drying capacity. This study is part of a wider research project: WGB_Shield (Shielding building' facades on cities revitalization. Triple-resistance for water, graffiti and biocolonization of external thermal insulation systems) that aims at the development of ETICS with improved durability in the urban environment. Further development on this issue are ongoing.*

Keywords: *ETICS, Durability, Mould Growth, Water Performance, ETAG 004.*

1 Introduction

The External Thermal Insulation Composite Systems (ETICS) are nowadays often used in Europe for new constructions and for thermal refurbishment of building facades (Barreira and Freitas, 2013). These systems present several advantages in comparison with other insulation solutions, such as the correction of thermal bridges, reduction of interior water condensation and increase of thermal efficiency, while maintaining the aesthetic appearance of the building, with relatively low installation cost and ease of application (Simona *et al.*, 2017). Nevertheless, biological growth has been identified as one of ETICS main disadvantages, with several ETICS facades showing this problem only few years after the building construction/intervention (Johansson *et al.*, 2010). Over time, biological growth causes cladding defacement, though it might not have major influence on the thermal performance of the system itself, however,

altering the aesthetic appearance of the building. This situation commonly leads to a disapproval of the building owner, ending up with several economic and social consequences, that limit the full implementation and a wider diffusion of ETICS (Johansson *et al.*, 2010).

Factors influencing mould growth on ETICS include nutrient availability, temperature, pH and moisture which seems to be the key factor (Johansson *et al.*, 2012). Extensive fungal development is linked to high levels of surface moisture content, resulting from the combined effect of surface condensation, drying process as well as from the finishing render composition. When the drying process is slow, the surface moisture content remains high for long periods, increasing the risk of biocolonization (Barreira and de Freitas, 2013). Thus, the main parameters affecting biological colonization on ETICS are thought to be the composition of the different elements (insulation material, base coat mortar and finishing coat) and the behaviour of the system concerning water absorption and drying. It is therefore essential to understand the hygrometric properties of ETICS and their composition in order to correlate them with biological growth.

2 Materials and Methods

2.1 Materials

Seven different ETICS solutions from three different manufactures were tested for mould growth and water behavior (capillary absorption and drying capacity). Table 1 briefly describes the selected materials. Detailed information about the formulation of each solution is not available due to industrial confidentiality.

Table 1. Characteristics of each system.

System (S) / Manufacture (M)	Thermal system (TI)	Finishing render (FR)*				S thickness (mm) = TI thickness + FR thickness
		Binder	Aggregates	Admixtures and additives	Finishing coat	
S1 / M1	EPS-1	Cement	Mineral fillers and resins	Not identified	Acrylic paint	S: 40.57 TI: 35.29
S2 / M1	EPS-1	Cement				S: 40.44 TI: 35.29
S3 / M2	ICB	Lime + hydraulic binders	Mineral fillers		Acrylic paint + pigment	S: 63.61 TI: 59.73
S4 / M2	EPS-2	Cement	Mineral fillers, resins, and synthetic fibres			S: 65.45 TI: 59.99
S5 / M3	ICB	Natural hydraulic lime +	Acrylic resins and mineral		Acrylic with siloxane resins	S: 41.91 TI: 37.91

		Mixed binders	fillers			
S6 / M3	EPS-2	Cement + Mixed binders				S: 43.30 TI: 38.30
S7 / M3	MW					S: 44.80 TI: 39.80
EPS: expanded polystyrene; ICB: expanded cork; MW: mineral wool. EPS-1 and EPS-2 were produced by different manufactures. *The FR includes a biocide						

Two types of samples were cut from the original ETICS panels of each system: the first was a set of 3 samples of each system with dimensions of 40 mm × 40 mm × S thickness (Tab. 1), which was used to assess mould growth; the other is described in Table 2 and was used to assess capillary absorption and drying capacity of each system. The total thickness of each system ranges between 40.44 mm and 65.45 mm and is presented in Table 1. The thermal insulation materials of each solution were also individually tested for mould growth. There are four types of insulation materials, including mineral wool (MW), expanded polystyrene from two different manufactures (EPS-1 and EPS-2) and expanded cork (ICB). The dimensions of these samples are 40 mm × 40 mm × TI thickness (Tab. 1).

Table 2. Materials, samples and laboratory tests for water behavior assessment.

Test	Reference	Sampling [Samples × S]	Dimensions [mm]
Capillary absorption	ETAG 004 (2013)	2 × 7	150 × 150 × TI thickness
Drying	EN 16322 (2013)	2 × 7	150 × 150 × TI thickness

2.2 Mould Growth Tests

The resistance of the different ETICS and insulation materials to mould growth was assessed using a method adapted from ASTM D 5590-17 (2017) and ASTM C1338-19 (2019) and previously described by Santos *et al.* (2017). Three replicates of each ETICS solutions and corresponding thermal insulation were tested.

Three fungal species were used in this study: spore suspensions of *Aspergillus niger* and *Penicillium funiculosum*, applied together, and *Aureobasidium pullulans*, applied alone. These species were chosen due to their widespread presence in interior and outdoor environments and commonly referenced in the literature and standards (Hoang *et al.*, 2010; ASTM D 5590-17, 2017; Verdier *et al.*, 2014). A volume of 2 ml of each spore suspension was uniformly distributed on the surface of the previously sterilized specimens and controls and the surrounding culturing media (4% malt, 2% agar). The controls were 3 replicates of Whatman n° 1 filter paper (45 mm diameter) and 3 wood samples (*Pinus pinaster*) with dimensions 40 mm × 40 mm × 10 mm, that allowed the validation of the test (ASTM C1138-19, 2019). After inoculation, the test flasks were incubated at a temperature of 22 ± 1°C and 70 ± 5% RH for a period of four weeks. A third group of test specimens was exposed in the same conditions but without any sterilization or inoculation thus allowing their natural inocula to potentially develop. Each week, the samples were visually rated for mould growth using the scale defined in Table 3. At the end of the exposure period the samples were removed from the flasks and the final percentage of contaminated surface (Table 3) was evaluated with the help of a stereo microscope.

Table 3. Rate of fungal (mould) development as defined in ASTM D 5590-17 (2017).

Rating	Description	Percentage of contaminated surface
0	None	0%
1	Traces of growth	<10%
2	Light growth	10 to 30%
3	Moderate growth	30 to 60%
4	Heavy growth	>60%

2.3 Capillary Absorption and Drying Tests

Water performance of ETICS was assessed through capillary absorption and drying capacity.

Capillary absorption tests were performed according to ETAG 004 (EOTA, 2013) in a conditioned room ($T = 23 \pm 2^\circ\text{C}$ and $65 \pm 5\% \text{ RH}$). A total of four cycles (each cycle has 24h with measurements at 3 min, 1, 4, 8 and 24h) of capillary absorption were conducted. Capillary water absorption coefficient was obtained by the slope of the initial phase of the curve that expresses the water absorption as a function of square root of time.

Drying test was performed following the recommendations of EN 16322 (2013) and started immediately after the capillarity test. The test was performed in a conditioned room ($23 \pm 2^\circ\text{C}$ and $65 \pm 5\% \text{ RH}$). Samples were weighted after determined periods of time until the variation of mass was constant for all samples. Two drying phases were determined: DR1 – the first drying phase, obtained by the negative slope of the initial linear section of the drying curve plotted with time in abscissa; and DR2 – the second drying phase, calculated by the negative slope of the linear section of the drying curve, plotted against the square root of time in abscissa. Drying index (DI) was obtained by Equation (1), in which M_x is the mass of the sample registered during the drying process (g), M_I is the mass of the sample in a dry state (g), M_3 is the mass of the sample in a saturated state (this mass corresponds to the mass at the beginning of the drying process (t_0)), t_f is the time at the end of the drying process.

Register for free at <https://www.scipedia.com> to download the version without the watermark

$$DI = \frac{\int_0^{t_f} \frac{M_x - M_I}{M_3 - M_I} dt}{\left(\frac{M_3 - M_I}{M_I}\right) \times t_f} \quad (1)$$

3 Results and Discussion

3.1 Resistance to Mould Growth

The results of the average rate of mould growth for ETICS surface finishing layer considering all type of inoculation were the same during or at the end of the test: zero (no growth). All controls (Whatman n° 1 filter paper and wood) were rated as 4 at the end of the 4-week testing which confirms the validity of the procedure. The fact that no growth occurs for any ETICS surface after 4 weeks of testing can be explained by the presence of biocide on the finishing render. Nevertheless, these are newly produced, unaltered sound systems, which were not subjected to any kind of aging or weathering procedures.

The results of the average rate of mould growth for the insulation materials are shown in Figure 1. After 4 weeks of incubation, significant mould growth was observed on the ICB samples, rated as 2 or more for every type of inocula (natural or artificial). For EPS-1 samples,

no growth was reported at any time during the test, however, for EPS-2, some samples presented traces of growth, especially with natural inocula. MW samples presented no growth for the *A. pullulans* inoculation and traces of growth since the first week of observations for the *A. niger* and *P. funiculosus* inoculation. Only one of the three MW tested samples showed traces of growth (rated as 1) after 4 weeks testing for natural inocula.

Register for free at <https://www.scipedia.com> to download the version without the watermark

Figure 1. Results of the average rate of mould growth for the insulation materials considering: (a) natural inocula (b) artificial inoculation with *A. niger* and *P. funiculosus* (c) artificial inoculation with *A. pullulans*.

Amongst the insulation materials, ICB samples presented the most intense mould growth. In fact, cork is a natural organic material with suberin, lignin and polysaccharides (cellulose and hemicellulose) in its composition (Knapic *et al.*, 2016). Organic or organic-based materials are more vulnerable to fungal deterioration since they provide ample nutrients, through their composition, contributing to fungal growth (Klamer *et al.*, 2004; Hoang *et al.*, 2010). Additionally, the results of rate of growth for ICB were significantly higher when inoculated with *A. niger* and *P. funiculosus* rather than *A. pullulans*.

In general, MW and EPS samples present a good resistance to mould attack, always presenting a rate of growth lower or equal to 1. Concerning MW, as an inorganic material, the susceptibility to mould growth is naturally lower than that of organic materials. The only sample rated as 1 for natural inocula could have been previously contaminated with some organic dust particles, that contributed to the increase of mould growth susceptibility (Jerábková and Tesarová, 2018). Regarding EPS, the resistance to fungal growth is noteworthy, which is in accordance with the results obtained by Jerábková and Tesarová (2018).

All insulation materials presented higher mould growth for natural inocula than for artificial inoculation. If, on the one hand, natural inocula can be more representative of real conditions (Hoang *et al.*, 2010), artificial inoculation significantly accelerates the test while improving repeatability and comparison between materials (Johansson *et al.*, 2012, 2014).

3.2 Capillary Water Absorption and Drying

The results obtained for capillary absorption and drying are shown in Table 4 and Figure 2. Sample S3 presents the highest value of capillary absorption at 1h and 24h, whereas sample S1 presents the lowest values. In fact, samples S1 and S2, both with cement-based matrix in the base coat and from the same manufacturer, presented lowest capillary water absorption, and, as a consequence of low water content, also the fastest drying capacity. Sample S1 presented not only the lowest values of capillary absorption at 1h and 24h but also the lowest value of capillary water absorption coefficient.

Figure 2. Capillary absorption curves (a) and drying curves (b).

Register for free at <https://www.scipedia.com> to download the version without the watermark

By comparing the capillary water absorption coefficient (C) obtained for sample S5 and S6, it was noticed an increase of 65% of the value of C for S5 in relation to S6. These samples present the same composition of finishing render with exception of the binder (S5 has natural hydraulic lime and mixed binders while S6 is composed of cement and mixed binders).

All samples achieved values of capillary absorption after 1h testing that are lower than 1 kg/m², which is the value required by ETAG 004 (EOTA, 2013). In fact, for all tested solutions, the highest level of capillary absorption happens in the first hour of test (even in the first 3 min), followed by a stabilization of the capillary water absorption. Therefore, all solutions have an adequate performance with regards to capillary absorption and drying, presenting low values of capillary absorption.

The results obtained for drying test are in line with those obtained for capillary water absorption, since samples that generally absorb more water are those that present higher drying rates, allowing fast removal of absorbed water. Additionally, a high correlation was obtained between the capillary absorption coefficient and drying rate 2 ($R^2 = 0.77$).

Table 4. Capillary absorption and drying test results.

System (S)	Capillary absorption				Drying		
	Capillary absorption 1h (kg/m ²)	ETAG 004 (≤ 1 kg/m ² at 1h)	Capillary absorption 24h (kg/m ²)	C (kg/m ² .min ^{0.5})	DR1 (kg/m ² .h)	DR2 (kg/m ² .h ^{0.5})	DI
S1	0.062	✓	0.242	0.019	0.0030	0.0197	1.05
S2	0.118	✓	0.379	0.034	0.0068	0.0396	1.02
S3	0.959	✓	1.268	0.184	0.0151	0.0989	1.01
S4	0.667	✓	1.217	0.115	0.0169	0.1099	0.94
S5	0.227	✓	0.669	0.081	0.0095	0.0619	1.00
S6	0.154	✓	0.385	0.049	0.0051	0.0335	1.00
S7	0.419	✓	0.832	0.151	0.0111	0.0773	0.98

4 Conclusions

With the aim of evaluating the resistance of different ETICS surface finishing layer and insulation materials to mould growth under laboratory conditions, 7 different ETICS solutions were tested considering three different types of inoculation. The thermal insulation materials of each solution were also individually tested for mould growth. Additionally, capillary water absorption and drying capacity of each ETICS were assessed.

The main conclusions of this study are the following:

- No mould growth was detected on any ETICS surface finishing layer after 4-week testing though it should be noticed that the materials were tested without previous aging or weathering procedures.
- Considering the thermal insulation materials tested individually for mould growth, ICB samples were the ones obtaining the highest level of mould growth after 4-week of incubation. For EPS-1 samples, no growth was reported at any time during the test. However, this is not the case for the EPS-2, where some samples presented traces of growth, especially when considering the natural inocula. MW samples presented no growth for the *A. pullulans* inoculation but traces of growth for the mixed spore suspension. However, as stated in the previous point, these differences in the insulation materials didn't visibly affect the full system behavior.
- All insulation materials presented higher mould growth for natural inocula than for artificial inoculation with either of the spore suspensions.
- All tested ETICS solutions showed good performance regarding capillary water absorption and drying capacity, with all solutions accomplishing the ETAG 004 requirements. Such good characteristics could be one of the reasons why, at this stage, the susceptibility of some insulation materials to mould growth didn't affect the performance of the full system. However, further tests are necessary to assess the moisture transport properties of ETICS after natural and artificial aging and compare those values with the ones presented in this study.

The results obtained in the present study give an overview on ETICS characteristics (capillary absorption, drying capacity and composition of ETICS layers) that might affect surface mould development. The next step in the research will consist on verifying ETICS durability by natural and artificial aging tests, which will affect ETICS finishing coat, possibly

leading to a higher susceptibility of the system to mould growth.

Acknowledgements

The authors gratefully acknowledge the support given by Portuguese Foundation for Science and Technology (FCT) within research project PTDC/ECI-EGC/30681/2017 (WGB_Shield – Shielding building' facades on cities revitalization. Triple resistance for water, graffiti and biocolonization of external thermal insulation systems).

ORCID

João Luís Parracha: <https://orcid.org/0000-0001-6214-3400>

Giovanni Borsoi: <https://orcid.org/0000-0002-2194-4620>

Maria do Rosário Veiga: <https://orcid.org/0000-0002-7135-8603>

Lina Nunes: <https://orcid.org/0000-0001-6849-3241>

References

- ASTM D 5590-17 (2017). Determining the resistance of paint films and related coatings to fungal defacement by accelerated four-week agar plate assay. ASTM International, Pennsylvania, USA
- ASTM C1338-19 (2019). Standard test method for determining fungi resistance of insulation materials and facings. ASTM International, Pennsylvania, USA
- Barreira, E. and Freitas, V.P. (2013). Experimental study of the hygrothermal behaviour of External Thermal Insulation Composite Systems (ETICS). *Building and Environment*, 63, 31-39. doi: 10.1016/j.buildenv.2013.02.001
- EN 16322 (2013). Conservation of Cultural Heritage – Test methods – Determination of drying properties. European Committee for Standardization, Brussels, Belgium
- EOTA (2013). Guideline for european technical approval of external thermal insulation composite systems with rendering. ETAG 004. Brussels, Belgium
- Hoang, C.P., Kinney, K.A., Corsi, R.L. and Szaniszlo, P.J. (2010). Resistance of green building materials to fungal growth. *International Biodeterioration & Biodegradation*, 64, 104-113. doi: 10.1016/j.ibiod.2009.11.001
- Jerábková, E. and Tesárová, D. (2018). Resistance of various materials and coatings used in wood constructions to growth of microorganisms. *Wood Research*, 63, 993-1002.
- Johansson, S., Wadsö, L. and Sandin, K. (2010). Estimation of mould growth levels on rendered façades based on surface relative humidity and surface temperature measurements. *Building and Environment*, 45, 1153-1160. doi: 10.1016/j.buildenv.2009.10.022
- Johansson, P., Ekstrand-Tobin, A., Svensson, T. and Bok, G. (2012). Laboratory study to determine the critical moisture level for mould growth on building materials. *International Biodeterioration & Biodegradation*, 73, 23-32. doi: 10.1016/j.ibiod.2012.05.014
- Johansson, P., Ekstrand-Tobin, A. and Bok, G. (2014). An innovative test method for evaluating the critical moisture level for mould growth on building materials. *Building and Environment*, 81, 404-409. doi: 10.1016/j.buildenv.2014.07.002
- Klamer, M., Morsing, E. and Husemoen, T. (2004). Fungal growth on different insulation materials exposed to different moisture regimes. *International Biodeterioration & Biodegradation*, 54, 277-282. doi: 10.1016/j.ibiod.2004.03.016
- Knapic, S., Oliveira, V., Machado J.S. and Pereira H. (2016). Cork as a building material: a review. *European Journal of Wood and Wood Products*, 74, 775-791. doi: 10.1007/s00107-016-1076-4
- Santos, T., Nunes, L. and Faria P. (2017). Production of eco-efficient earth-based plasters: Influence of composition on physical performance and bio-susceptibility. *Journal of Cleaner Production*, 167, 55-67. doi: 10.1016/j.jclepro.2017.08.131
- Simona, P.L., Spuru, P. and Ion, I.V. (2017). Increasing the energy efficiency of buildings thermal insulation. *Energy Procedia*, 128, 393-399. doi: 10.1016/J.EGYPRO.2017.09.044
- Verdier, T., Coutand, M., Bertron, A. and Roques, C. (2014). A review of indoor microbial growth across building materials and sampling and analysis methods. *Building and Environment*, 80, 136-149. doi: 10.1016/j.buildenv.2014.05.030

Register for free at <https://www.scipedia.com> to download the version without the watermark