Behavior of Mortars with Different Porosities in Front of Attack of Aggressive Agents

Alessandra M. Weber¹, Wellington Mazer², Daniela E. Pedroso³ and Cleber Pedroso⁴

¹ Academic Department of Civil Construction, Federal and Technological University of Parana (UTFPR), Campus Ecoville, Curitiba, Brazil, alessandramoniqueweber@gmail.com

² Academic Department of Civil Construction, Federal and Technological University of Parana (UTFPR), Campus Ecoville, Curitiba, Brazil, wmazer@utfpr.edu.br

³ Academic Department of Civil Construction, Federal and Technological University of Parana (UTFPR), Campus Ecoville, Curitiba, Brazil, danievaniki@hotmail.com

⁴ Academic Department of Civil Construction, Federal and Technological University of Parana (UTFPR), Campus Ecoville, Curitiba, Brazil, cleber.ped@gmail.com

Abstract. *Chemical reactions that lead to decreased durability in concrete structures may result from chemical interactions between aggressive agents present in the external environment and cement paste compounds or may result from internal reactions. The chemical reactions are manifested by the physical properties of the concrete, such as porosity and permeability and the decrease of resistance and cracking. Among the several aggressive agents that attack the reinforced concrete structures it can be highlighted chloride ions, sulphate ions and carbon dioxide. In this context, the study presents the analysis of different traces of mortar executed with cement type CPII-F-32 (OPC Cement, in Brazil one of the most used cements) with w/c ratios of 0.4 and 0.7, when subjected to the attack of sulphates, chlorides and carbonation. The analyzes quantitatively evaluated the amount of ions present after exposure to the agents and demonstrate the importance of evaluating the dosage of water in the mortars to minimize future problems with durability.*

Keywords: *Mortars, Sulphate Attack, Chloride Attack, Carbonation, Porosity.*

1 Introduction

Chemical reactions leading to decreased durability in concrete structures may result from chemical interactions between aggressive agents present in the external environment and cement paste compounds or may result from internal reactions like alkali-aggregate reaction, or from reaction of delayed hydration CaO and MgO crystalline, if present in excessive amounts in Portland cement, or electrochemical corrosion of concrete reinforcement. Chemical reactions manifest themselves through the physical failures of concrete such as porosity and permeability, decreased strength and cracking.

Among the various aggressive agents that attack reinforced concrete structures, chloride ions, sulphate ions and carbon dioxide can be highlighted.

Sulphate can be found in soils such as landfills and is a major cause of degradation of cement-based materials. The attack by sulfate ions stands out especially when dealing with marine, underground or sewage handling structures (Mehta and Monteiro, 2014; Wei *et al.*, 2019).

When dissolved sulfate ions (SO_4) react with hydrated cement paste the two main means of

sulfate attack are: reaction with hydration products of unhydrated tricalcium aluminate (C_3A) producing ettringite and reaction with calcium hydroxide producing gypsum. Sulfate attack on concrete can manifest as expansion or cracking, leading to increased concrete permeability, structural problems and initiating corrosion processes of reinforcement (Mehta and Monteiro, 2014).

According Mangat and Ojedokun (2019) the chloride concentration of concrete exposed to a chloride environment is a parameter used to characterize the long term chloride resistance of concrete. The presence of chlorides is a cause of the corrosion process in reinforcement of reinforced concrete structures. The structure in an environment that has seawater, sea salt and thaw salts is subject to attack by chlorides. The rate of chloride penetration from the surface to the interior of the concrete depends on: the amount of chloride ions in the environment, the permeability of the concrete and the humidity of the environment (Aguiar, 2011).

Carbonation of concrete is directly linked to the CO_2 diffusion coefficient that is determined by Fick's first law, but there are limitations in some parameters, for example CO_2 diffusivity varies over time and strongly depends on the moisture content of the pores. concrete, as well as other variables that may also influence the microstructure of the concrete, such as cure condition, moisture content, location, elapsed time and mixing parameters (Yoon *et al.*, 2007).

In this context, the objective is to analyze different traces of mortars made with type CP II – F32 cement with w/c factors of 0.4 and 0.7 when subjected to the attack of sulfates, chlorides and carbonation.

2 Materials and Methods

To evaluate the durability, the specimens were exposed for 70 days to aggressive agents to verify their performance against the attack of sulfate ions, chlorides and carbonation. For the evaluation, quantitative tests were performed. The tested mortar has a 1:3 trait (cement: sand), varying the water/cement ratio in two levels, being 0.4 to obtain less porous mortar and w/c of 0.7 for a more porous mortar. In samples with w/c of 0.4, 1% hyperplasticizer was added to aid in the consistency of the mortar.

The binder used was Portland Cement CP II – F32, chosen for its wide availability in the market. The choice of producing mortars is due to the fact of ease in smaller samples, in this case it was decided to mold 10 x 5 cm cylindrical specimens. According to some authors such as Papadakis (2000), Kulakowski (2002), Gervais *et al.* (2004), Pauletti *et al.* (2007), Pauletti (2009) and Neville (2015) explain about better results that the use of mortar brings in the carbonation front analysis, such as the influence of the presence of coarse aggregate.

For durability analysis against the aggressive agents the specimens were submitted after cure of 28 days in a humid chamber, for the sulfate solution was used 10% magnesium sulfate ($MgSO_4$). For the accelerated chloride attack, 10% sodium chloride ($NaCl$) solution was added and for carbonation depth evaluation, the specimens were deposited in a carbonation chamber with 10% controlled CO_2 concentration, without the control of humidity and temperature.

2.1 Sulphate Content

The samples were fully submerged in magnesium sulphate (MgSO_4) solution of 10% for up to 70 days. The chemical test to determine the sulphate ions content in the samples was made according to an adaptation of the standard APHA Method 4500- SO_4^{2-} (1997). The procedure consists to submit the ground sample, whose diameter is less than $600\text{ }\mu\text{m}$, to a solution of hydrochloric acid (HCl), shown in Figure 1, with barium chloride (BaCl_2), which will form a precipitate of barium sulphate (BaSO_4), which after calcination at 800°C is heavy (M_{calcined}).

Figure 1. On the left the sample mixture with hydrochloric acid and on the right the filtered solution.

To determine the percentage of sulphate in the sample, the equation is:

$$\text{SO}_3(\%) = \frac{34,3045 \cdot M_{\text{calcined}}}{M_{\text{standard}}} \quad (1)$$

Where the mass of the standard sample is weighed prior to the test in grams.

Register for free at <https://www.scipedia.com> to download the version without the watermark

2.2 Chloride Concentration

The chloride concentration of the mortar powder sample was obtained Volhard's titration method. The procedure consists an indirect titration to determine the chloride ion that precipitates with silver ion (Figure 2).

The acid soluble chloride content was calculated as a percentage of chloride ions by weight of the binder, by the following equation:

$$\text{Cl}(\%) = 0,1773 \cdot \frac{V_2 - V_1}{m_1} \quad (2)$$

Where V_1 is the volume of ammonium thiocyanate of a standard sample in ml, previously determined to be 0,07; V_2 is the volume of ammonia thiocyanate in the concrete sample in ml; and m_1 is the mass of the concrete sample in grams.

Figure 2. Silver chloride solution filtration and coagulation after boiling and then titanium ammonium titration.

2.3 Carbonation Penetration

Carbonation tests were performed by cylindrical mortar samples. Phenolphthalein was used as test to carbonation penetration. It is in the initiation phase that it was intended to verify the occurrence of carbonation, because generally the typical appearance of carbonation is the occurrence of light spots produced by refraction of calcium carbonate, it is necessary to verify the carbonation using colorimetric indicators that point the pH. The lower the pH, the lighter its appearance, tending to colorless in the less alkaline regions. A non-carbonated concrete in the most alkaline region turns purple when using this same indicator. The most commonly used carbonation or pH indicator is the phenolphthalein solution or equivalent, being successfully used for pH between 8 and 11.

Figure 3 shows the color of the specimen when the phenolphthalein solution is sprayed.

Register for free at <https://www.scipedia.com> to download the version without the watermark

Figure 3. Specimens submitted to the phenolphthalein spray test.

3 Results

The average values of the analyzes of the three tests performed for the sample group, considering the w/c variations are presented in Table 1.

Table 1. Mean values for durability analyzes.

Specimens		Sulphate content (%)	Chloride content (%)	Carbonation Penetration (mm)
CP II – F32	w/c 0.4	6.28	0.55	-
	w/c 0.7	8.39	0.69	2.1

Sulphate content increased by more than 33% when the water factor used in the mortar was added.

CP II – F32 cement analysis for chloride determination by chloride submerged samples resulted in chloride content of 0.69% for samples with water/cement ratio of 0.7 and 0.55% for samples with water/cement ratio of 0.4. According to NBR 12655 (ABNT, 2015) the maximum chloride content for reinforced concrete exposed to chloride in the service conditions of the structure is 0.15% (considering aggressive classes III and IV, which includes marine and industrial environments with chemical agents). Therefore, all the samples exceeded this reference.

It was not possible to measure the carbonation depth for the samples with water/cement ratio of 0.4 because no sufficiently measurable points were observed for the caliper measurement. For the trace with w/c 0.7 the average carbonation point was 2.1 mm.

4 Conclusions

- OPC cement mortars using w/c fractions of 0.4 show better durability results when compared to 0.7 water/cement ratio.
- The proposed tests serve as durability indicators for previous considerations due to the attack of sulfates, chlorides and carbonates.
- The service life of concrete structures depends mainly on the durability of the concrete. Concrete made from traditional Portland cement is considered a durable material for the non-aggressive environment, however water should be carefully considered as a direct influence on the durability of mortars and concretes, due to the increased porosity.

ORCID

Alessandra M. Weber: <http://orcid.org/0000-0002-0991-1842>

Wellington Mazer: <http://orcid.org/0000-0002-9941-999X>

Daniela E. Pedroso: <http://orcid.org/0000-0003-3077-4544>

Cleber Pedroso: <http://orcid.org/0000-0002-8265-2920>

References

- ABNT (2015). *NBR 12655: Concreto de cimento Portland - Preparo, controle, recebimento e aceitação – Procedimento*, Rio de Janeiro, Brasil.
- Aguiar, J.E. (2011). *Durabilidade, proteção e recuperação das estruturas*, Class Notes, Escola de Engenharia da

- Universidade Federal de Minas Gerais, Belo Horizonte, Brasil.
- APHA, (1997). *Method 4500-SO₄²⁻ - Sulfate*. Standard Methods for the Examination of Water and Wastewater. American Public Health Association.
- Gervais, C., Garrabrants, A.C., Sanchez, F., Barna, R., Moszkowicz, P. and Kosson, D.S. (2004). The effects of carbonation and drying during intermittent leaching on the release of inorganic constituents from a cement-based matrix. *Cement and Concrete Research*, 34 (1), 119-131. doi: 10.1016/S0008-8846(03)00248-5
- Kulakowski, M.P. (2002). *Contribuição ao estudo da carbonatação em concretos e argamassas compostos com adição de sílica ativa*, PhD Thesis, Universidade Federal do Rio Grande do Sul, Porto Alegre, Brasil.
- Mangat, P.S. and Ojedokun, O.O. (2019). Bound chloride ingress in alkali activated concrete. *Construction and Building Materials*, 212, 375–387. doi:10.1016/j.conbuildmat.2019.03.302
- Mehta, P.K. and Monteiro, P.J. (2014). *Concreto: microestrutura, propriedades e materiais*. São Paulo: IBRACON.
- Neville, A.M. (2015). *Propriedades do Concreto*. Brasil: Bookman Editora.
- Papadakis, V. G. (2000). Effect of supplementary cementing materials on concrete resistance against carbonation and chloride ingress. *Cement and concrete research*, 30(2), 291-299. doi: 10.1016/S0008-8846(99)00249-5
- Pauletti, C. (2009). *Estimate of natural carbonation of cement materials based on accelerated tests and prediction models*, PhD Thesis, Universidade Federal do Rio Grande do Sul, Porto Alegre, Brasil.
- Pauletti, C., Possan, E. and Dal Molin, D.C.C. (2007). Carbonatação acelerada: estado da arte das pesquisas no Brasil. *Ambiente construído*, 7 (4), 7-20.
- Wei, L., Xiao-Guang, J. and Zhong-Ya, Z. (2019). Triaxial test on concrete material containing accelerators under physical sulphate attack. *Construction and Building Materials*, 206, 641-654. doi: 10.1016/j.conbuildmat.2019.01.186
- Yoon, I.S., Çopuroğlu, O. and Park, K.B. (2007). Effect of global climatic change on carbonation progress of concrete. *Atmospheric environment*, 41 (34), 7274-7285. doi: 10.1016/j.atmosenv.2007.05.028

SCIPEDIA

Register for free at <https://www.scipedia.com> to download the version without the watermark